

EL 245

UV LAMINATING ADHESIVE

DESCRIPTION	Low viscosity adhesive for OPP lamination of papers and other substrates.
PROPERTIES	Good adhesive properties High reactivity Low viscosity Good adhesion
APPLICATION	Stir well before use Anilox 120-160 l/cm Film weight 4-8 g/cm ³ Rollers EPDM UV lamps minimum 80 w/cm
SUBSTRATES	Coated paper and board Treated/primed polyethylene Treated/primed polypropylene
FILM	Treated OPP
STORAGE & HANDLING	Store at temperatures between 5°C and 25°C. Protect from sunlight. In unopened containers EL245 has a shelf life of 6 months.
PACKAGING	5kgs, 200kgs, 1000kgs
AUXILIARY PRODUCTS	RLA 350 UV wash up

DISCLAIMER

The information contained in this data sheet is correct to the best of our knowledge. It is intended as a guide only for the optimum use of the named product(s) and is not intended as a warranty or as a specification. This datasheet may not be suitable for combinations with other materials or in processes other than those specifically described. The user should always make their own tests to establish that the product(s) meets their requirements.